



## MANUFACTURER'S SPECIFICATIONS:

### DuraDeck Surfacing System

## Part 1 – GENERAL

### 1.1 SCOPE:

Provide all materials, labor, and equipment necessary to install the DuraDeck Surfacing System.

### 1.2 DESCRIPTION:

DuraDeck is a UV resistant, porous, non-slip surface designed for use in walkways, run-and-play, and deck applications.

### 1.3 COMPOSITION:

DuraDeck consists of:

- A. Colored rubber made of Thermoplastic Vulcanizate (TPV) mixed with
- B. Aromatic or Aliphatic Polyurethane binder.

### 1.4 QUALITY ASSURANCE:

- A. Qualifications
  - 1. The Applicator/ Installer shall be trained and approved by DuraPlay, Inc.
  - 2. All components of the DuraDeck Surfacing System shall be obtained from DuraPlay, Inc. or its authorized distributors. No substitutions or additions of other materials shall be submitted without prior written permission from DuraPlay, Inc.
  - 3. Acceptable substrates for DuraDeck include asphalt or heavy broom finished concrete.
  - 4. Other substrates must be approved by DuraPlay, Inc. in writing prior to application.

### 1.5 SUBMITTALS:

- A. Material product data
- B. DuraPlay Color Chart
- C. Sample colors if needed
- D. Warranty
- E. Product Liability Insurance Certificates



150 Brownson Lane, Driftwood, TX 78619

## **1.6 DELIVERY, STORAGE and HANDLING**

- A. Deliver all materials in original unopened packages with labels intact.
- B. Store all materials protected from weather and at temperature not less than 40° F (4°C).

## **1.7 JOB CONDITIONS:**

- A. Ambient air temperature shall be 45 degrees or greater and rising at the time of installation of the surface and shall remain at 33 degrees or greater for at least 48 hours after application.
- B. Adjacent materials and the Surface shall be protected during installation, while curing and unattended, from weather and other damage.

## **1.8 ALTERNATES AND ALLOWANCES:**

- A. Systems to be considered equal to those specified herein shall be approved by the architect, in writing, at least ten working days prior to the project bid date.

# **Part 2 – PRODUCTS**

## **2.0 GENERAL**

All material components of the DuraDeck Surfacing System shall be obtained from the same manufacturer or its authorized distributors.

## **2.1 MATERIALS:**

- A. DuraPlay Primer: A single-component moisture-curing polyurethane primer.
- B. DuraPlay Binder: An elastic aromatic or aliphatic polyurethane pre-polymer, UV resistant, low odor, capable of excellent weathering and binding characteristics.
- C. Duraplay TPV Rubber: A manufactured rubber having a density of 1 to 4mm.
  - 1. Available in standard colors: terra cotta, blue, green, beige, black and premium colors: red, bright green, dark green, purple, light blue, azure, turquoise, cream, brown, earth yellow, yellow, orange, charcoal, grey, light grey, pink (colors subject to change).
  - 2. Available in any mixture of above colors.
  - 3. Thickness is nominal 1/2" or 2.2 lbs per square foot.

## **2.2 TECHNICAL INFORMATION:**

- A. Applicable Standards
  - 1. Non-slip characteristics under ASTM-E-303
  - 2. Flammability under 8S -5696 and ASTM-D-2859
  - 3. Tensile strength (ASTM D412) - 60 psi
  - 4. Tear resistance (ASTM D624) – 140%
- B. Chemical Properties
  - 1. 79% TPV(color) Rubber Granules, 21% Aromatic or Aliphatic Binder



150 Brownson Lane, Driftwood, TX 78619

## 2.3 INSTALLATION:

- A. Inspection: Prior to application of DuraDeck Surfacing System, the substrates shall be examined for compliance with the contract document of DuraPlay specifications. The general contractor and architect shall be advised of all discrepancies. Work shall not proceed until unsatisfactory conditions are corrected.
- B. Sub -Surface Preparation
  - 1. New or existing Concrete: Must be cured at least 28 days. All concrete must have a heavy broom finish.
  - 2. Asphalt must cure for at least 28 days. Scrub with degreaser to remove any surface oils.
  - 3. Drains, doorways or entryways shall be raised 1/2" and perforated on the sides to allow water to drain under the surface.
  - 4. For flush mounted drains, doorways and entryways, cut a 3/8 inch x half inch keyway groove into the concrete surrounding the object.
- C. Duraplay Primer:
  - 1. Apply primer by spray or short nap roller at the rate of 300 square feet per gallon. Do not oversaturate substrate. Prime entire area to be surfaced and any adjacent vertical barriers such as playground equipment support legs, curbs or edging that will contact the surfacing system.
- D. DuraDeck Surfacing System:
  - 1. Apply mixed binder/granule at 9/16" using a screed bar or guide.
  - 2. Using a steel pool trowel, even rubber/granule mixture. Be sure to continuously lubricate trowel with kerosene, diesel fuel or soapy water.
  - 3. As the mixture is leveled, apply a downward pressure onto the surface so that the mixture compacts tightly.
  - 4. Check surface to be level.
  - 5. Allow to cure for a minimum of 72 hours prior to usage. At the end of the minimum curing period, verify that the top surface is sufficiently dry and firm to allow foot traffic and use without damage to the surface. Do not allow foot traffic or use of the surface until it is sufficiently cured.
- E. Edge Detail:
  - 1. See [www.duraplay.com](http://www.duraplay.com) or request pdf.

## 2.4 WARRANTY:

Standard warranty period is 3 years from the date of completion for all DuraDeck Surfaces.

## 2.5 PROTECTION:

It is the responsibility of the customer to provide security to protect the drying surface from footprints and vandalism.



150 Brownson Lane, Driftwood, TX 78619

## 2.6 CLEANING AND MAINTENANCE:

DuraPlay Safety Surfaces, like any flooring material, require periodic cleaning. The frequency of cleaning depends on the intensity and type of traffic on the surface. DuraPlay Surfaces are self-sufficient; therefore, excessive cleaning is needed only when outside contaminants are introduced. In some cases, dissolved salts in water ("hard water") or the environment can cause a whitish film to develop on the DuraSplash Surface. If this occurs, immediate cleaning is necessary to enhance the original colors of the surface.

### A. The Cleaning Process:

1. For "whitish" film or mildew deposits, we recommend using Soft Scrub with Bleach to clean the surface.
2. Initially dilute the Soft Scrub at a proportion of 1 part cleanser to 2 parts water and mix well.
3. Scrub the surface with a stiff-bristled scrub brush. Rinse well with water.
4. If the stains persist, repeat the process above with a 1 to 1 cleanser/ water ratio.
5. For excessive residue, use the cleanser without diluting.
6. Another method of cleaning is pressure washing with a light spray nozzle (caution – heavy spray nozzles may damage surface).

V:4.22



150 Brownson Lane, Driftwood, TX 78619